

12 Lysander Close, Pysons Road Ind. Est.,
Broadstairs, Kent CT10 2YJ
Telephone: (01843) 604896 (5 Lines)
Fax: (01843) 862388
e-mail: sales@davidbaileyfurniture.co.uk
www.davidbaileyfurniture.co.uk

CONTRACT FURNITURE

STANDARD LAMINATE DOOR AND WORKTOP COLOURS




D021 | POMMIER DE DEAUVILLE



E028 | ÉRABLE NORDIQUE



S040 | CÉRUSÉ CLAIR



C127 | CHÊNE GIVERNY



H025 | POMMIER DE HONFLEUR



H027 | HÊTRE DE PROVENCE



D018 | CHÊNE DE MEYMAC




M007 | MERISIER RUSTIQUE




N010 | NOYER PERLÉ




Z002 | ZEBRA MOKA



B099 | BRUSHED METAL




M003 | MARYLAND FONCÉ



M001 | MARYLAND CLAIR



B133 | BÉTON BULLÉ



B092 | BROSSÉ GRIS



N023 | NOVA SAPHIR

Other colours available on request



LAMINATES MANUFACTURED
TO
BS EN438



**polyrey**[®]

DAVID BAILEY

FURNITURE SYSTEMS LIMITED

High Pressure Laminate (HPL) Technical Data		Postforming Grade		
Thickness Classification BSEN 438 Resistance to boiling water 2hrs at 100°C EN 438-2-7 - Mass - Thickness Resistance to steam EN 438-2-24 Superficial heat resistance EN 438-2-8: 180° cooled for 20 minutes Colour fastness under artificial light EN 438-2-16 Chemical resistance (individual chart available on request) Impact resistance EN 438-2-11: Force of projection Scratch resistance Abrasion resistance EN 438-2: No. of revolutions Resistance to cigarette burns EN 438-2-18 Resistance to cracking EN 438-2-13 Fire rating Thermal conductibility factor λ Hygienic surface I.A.N.E.S.C.O. certification		0.8mm & 1mm HGP ≤ 17.5% ≤ 19.5% ≥ 3 No damage ≥ 6 No staining ≥ 20N ≥ 2N ≥ 350 No burns Class 4 Class 2 0.1 to 0.5kcal/m.h. °c Authorised		
Life Cycle Assessment (LCA)		1mm HPL per 1m²		19mm Chipboard per 1m²
Environmental Impact				
		Raw materials	Production	Raw materials and Production
Abiotic Depletion	10 ⁻¹⁵	12	3	20.5
Biotic Depletion	years	0	0	0
Greenhouse effect	Kg	4.5	1.4	9.5
Ozone layer depletion	10 ⁻⁷ kg	0.77	0.52	7.5
Energy	MJ	63	20	135.5
Waste	Kg	0.066	0.074	0.223
Source: Intron BV				
Abiotic Depletion -	Responsible treatment of HPL elements after their long life (thermal recovery) reduces the impact of abiotic resources by 68%.			
Biotic Depletion -	HPL elements do not deplete resources like wood. Their lifetime is longer than cultivated forests need to grow.			
Cleaning & Maintenance With clean cloths dipped in mild detergent. Stubborn stains can be removed by the use of a NON abrasive cleaner. Harsh scouring powders should be avoided. Fruit juices, bleaches and strong mineral acids should be wiped off immediately to avoid a more permanent stain. Please consult the manufacturer prior to removing very difficult stains.				

DAVID BAILEY FURNITURE SYSTEMS LTD

12 Lysander Close, Pysons Road Ind. Est., Broadstairs, Kent CT10 2YJ Tel: (01843) 604896
 Fax: (01843) 862388 e-mail: sales@davidbaileyfurniture.co.uk www.davidbaileyfurniture.co.uk